

BOPP Pearlized Film

-----Woven Plastic Matte Laminating Film

Typical values:

Testing items		Unit	Testing Method	Requirement
Thickness		μm	GB/T 6672-2001	15-80
Density		g/cm ³	GB/T 6343-2009/ISO 845:2006	≤0.8
Tensile strength at break	MD≥	MPa	GB/T 1040.3-2006/ISO 527-3:1995	55
	TD≥			110
Elongation at break	MD≤	%		160
	TD≤			60
Gloss	≥	%	GB 8807-88	50
Friction coefficient（no nstatic / static）	≤	-	GB/T 10006-2021/ISO 8295:1995	0.8
Heat sealing strength	≥	MPa	QB/T 2358-98	1.8(<35μ)
				2.5(>35μ)
Light transmittance	≤	%	GB/T 2410-2008	50
Surface tension	≥	mN/m	GB/T 14216-2008/ISO 8296:2003	38