

BOPP Pearlized Film

-----Flower Film

Typical values:

Testing items		Unit	Testing Method	Requirement
Thickness		μm	GB/T 6672-2001	64-66
Density		g/cm³	GB/T 6343-2009/ISO 845:2006	0.62-0.63
Tensile strength at break	MD≥	MPa	ASTM D-882	65
	TD≥			120
Elongation at break	MD≤	%		180
	TD≤			60
Heat shrinkage	MD≤	%	Hot water 120℃ 2 min	3
	TD≤			2
45°Gloss	≥	%	GB 8807-88	80
Friction coefficient	μs≤	-	ASTM D-1894	0.55
	μk≤			
Haze	≥	%	ASTM D-1003	95
Surface tension of one side	≥	mN/m	ASTM D-2578	39
Surface tension of the other side				43